

# Summary of Preparation and Use of WOODguard®

## NEW, WEATHERED, UNTREATED WOOD

### CLEANING RECOMMENDATIONS:

- Spray the surface with clean water, thoroughly wetting the wood.
- Generously apply a 4 oz. solution of **WOODguard Surface Prep** in one gallon of water using a garden pump sprayer.
- While the surface is still wet, scrub with a stiff-bristled nylon brush and keep the surface moist for 15 – 20 minutes. (Do not let the solution dry on the wood). This will clean and open the wood pores to really accept the **WOODguard®** treatment. For the best result, this is the preferred method to prepare the wood surface for **WOODguard**.
- Wash the surface with clean water from the top down using a low-pressure (<500 PSI) high water volume sprayer one foot from the surface.
- After the excess water has dripped off the wood, measure the pH of the water droplets on the bottom log or board. If the pH is the same as the rinse water, you may go to the next area. If the pH is greater than that of the rinse water, additional rinsing is necessary. [If all of the **WOODguard Surface Prep Solution** is not removed, the wood will turn a dark brown to black color]. Proper rinsing is a very important step.
- Let surface dry completely (moisture content below 18%). Usually after 3 days.

### APPLICATION:

- Apply **one coat** of **WOODguard** using a low-pressure garden sprayer from the top down. Apply to refusal (until **WOODguard** starts to run) and have someone follow to back brush the applied **WOODguard** to a smooth uniform coating. You will not have lapping marks if you overlap adjoining freshly painted areas.
- Clean tools with paint thinner or mineral spirits
- This treatment will give a long lasting finish of 2 – 7 years depending on how many applications have been applied, along with termite and decay protection.
- If additional surface protection is required and you require a brighter more reflective surface, apply a coat of **WOODguard TC™** (Top Coat). See the **WOODguard TC** Product Data Sheet for more information.

#### **ISK Biocides, Inc.**

416 E. Brooks Rd. - Memphis, TN 38109

Ph: 800-238-2523

Fax 901-344-5388

® WOODguard is a registered trademark of IBC Manufacturing Company.

™WOODguard TC is a trademark of IBC Manufacturing Company